

# ALUMINA 99.9%

ROHS & REACH COMPLIANT

---

## Physical properties

<b>DENSITY</b>	3.96 g/cm <sup>3</sup>
<b>COMPOSITION</b>	AL <sub>2</sub> O <sub>3</sub> 99.9%
<b>COLOUR</b>	cream

---

## Thermal properties

<b>SPECIFIC HEAT</b>	900 j/kg K (at 100°C)
<b>CONDUCTIVITY</b>	30 W/m .K (at 20°C)
<b>EXPANSION</b>	7.5 10 <sup>-6</sup> /K <sup>-1</sup>
<b>SHOCK RESISTANCE</b>	200°C
<b>MAX WORKING TEMPERATURE</b>	1500°C

---

## Mechanical properties

<b>HARDNESS</b>	1900 Vickers
<b>MODULUS OF RUPTURE</b>	2500 MPa
<b>POISSON'S RATIO</b>	0.23
<b>YOUNG'S MODULUS</b>	400 GPa
<b>FRACTURE TOUGHNESS</b>	5 MPa . m <sup>1/2</sup>
<b>COMPRESSIVE STRENGTH</b>	4000 MPa
<b>BENDING STRENGTH</b>	500 MPa

---

## Chemical properties

<b>ACID &amp; ALKALI</b>	excellent resistance
--------------------------	----------------------

---

## Electrical properties

<b>DIELECTRIC CONSTANT</b>	9.7 K at 1MHz
<b>RESISTIVITY</b>	5 10 <sup>14</sup> Ohm .cm (at 20°C)